

statements | TILE & STONE

Marvel X

Porcelain Tile

Thickness: 9mm

of Faces 24x24: Cal. Apuano - 33 Faces | Cal. Perla - 37 Faces | Cal. Sublime - 48 Faces
Fior - 39 Faces | Grey Cloud - 41 Faces

of Faces 24x48: Cal. Apuano - 26 Faces | Cal. Perla - 34 Faces | Cal. Sublime - 42 Faces
Fior - 30 Faces | Grey Cloud - 26 Faces

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	≤0.1%
Break Strength	C648	ISO-10545/4	S ≥1500 N R ≥40 N/mm ²
Scratch Hardness	MOH's Scale	EN-101	6-Matte ; 5-Polished
Chemical Resistance	C650	ISO-10545/13	A LA HA
Frost Resistance	C1026	ISO-10545/12	Resistant
Stain Resistance	C1378	ISO-10545/14	5
Fire Rating	E84	ISO-13501/1	Non Combustible
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	≤ 150 mm ³
Dynamic Coefficient of Friction (DCOF)	A137.1	-	≥ 0.50 / R10 (Matte)
Shade and Texture Rating	CTDA "V"	-	V2 (Cal. Apuano) V3 (all other colors)
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukwila, WA 98188