

statements | TILE & STONE

CC Mosaics + Penny Rounds

Porcelain Mosaic

Thickness: 6mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<= 0.5%
Break Strength	C648	ISO-10545/4	Min 290
Scratch Hardness	MOH's Scale	EN-101	3
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	--
PEI-Abrasion Resistance of Glazed Tile	C1027	ISO-10545/7	3
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.21
Shade and Texture Rating	CTDA "V"	-	V2
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukila, WA 98188

statements | TILE & STONE

CC Mosaics + Herringbone

Porcelain Mosaic

Thickness: 6mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<= 0.5%
Break Strength	C648	ISO-10545/4	Min 250
Scratch Hardness	MOH's Scale	EN-101	3
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	--
PEI-Abrasion Resistance of Glazed Tile	C1027	ISO-10545/7	3
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.22
Shade and Texture Rating	CTDA "V"	-	V1
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukila, WA 98188

statements | TILE & STONE

CC Mosaics + 2x4 Brick

Porcelain Mosaic

Thickness: 6mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<= 0.5%
Break Strength	C648	ISO-10545/4	Min 290
Scratch Hardness	MOH's Scale	EN-101	2
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	--
PEI-Abrasion Resistance of Glazed Tile	C1027	ISO-10545/7	2
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.21
Shade and Texture Rating	CTDA "V"	-	V2
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukila, WA 98188

statements | TILE & STONE

CC Mosaics + Hexagon

Porcelain Mosaic

Thickness: 5.4mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<= 0.5%
Break Strength	C648	ISO-10545/4	Min 290
Scratch Hardness	MOH's Scale	EN-101	3
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	--
PEI-Abrasion Resistance of Glazed Tile	C1027	ISO-10545/7	4
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.30
Shade and Texture Rating	CTDA "V"	-	V2
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukila, WA 98188

statements | TILE & STONE

CC Mosaics + Dots

Porcelain Mosaic

Thickness: 6mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<= 0.5%
Break Strength	C648	ISO-10545/4	Min 290
Scratch Hardness	MOH's Scale	EN-101	3
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	--
PEI-Abrasion Resistance of Glazed Tile	C1027	ISO-10545/7	4
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.30
Shade and Texture Rating	CTDA "V"	-	V2
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukila, WA 98188