

statements | TILE & STONE

CC Mosaics - Hexagon 1x1

Porcelain Tile

Thickness: 5.4mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<=0.5%
Break Strength	C648	ISO-10545/4	Min. 290
Scratch Hardness	MOH's Scale	EN-101	3
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	-
PEI-Abrasion Resistance of Glazed Tile	C1027	ISO-10545/7	4 & 2 (black)
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.30
Shade and Texture Rating	CTDA "V"	-	V2
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukwila, WA 98188

statements | TILE & STONE

CC Mosaics - Squares 1x1

Porcelain Tile

Thickness: 5.4mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<=0.5%
Break Strength	C648	ISO-10545/4	Min. 290
Scratch Hardness	MOH's Scale	EN-101	3
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	-
PEI-Abrasion Resistance of Glazed Tile	C1027	ISO-10545/7	4 & 2 (black)
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.32
Shade and Texture Rating	CTDA "V"	-	V2
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukwila, WA 98188

statements | TILE & STONE

CC Mosaics - Hexagon 2x2

Porcelain Tile

Thickness: 6mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<=0.5%
Break Strength	C648	ISO-10545/4	Min. 290
Scratch Hardness	MOH's Scale	EN-101	3
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	-
PEI-Abrasion Resistance of Glazed Tile	C1027	ISO-10545/7	4 & 2 (black)
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.40
Shade and Texture Rating	CTDA "V"	-	V2
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukwila, WA 98188

statements | TILE & STONE

CC Mosaics - Basket Weave

Porcelain Tile

Thickness: 6mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<=0.5%
Break Strength	C648	ISO-10545/4	Min. 290
Scratch Hardness	MOH's Scale	EN-101	3
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	-
PEI-Abrasion Resistance of Glazed Tile	C1027	ISO-10545/7	4 & 2 (black)
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.32
Shade and Texture Rating	CTDA "V"	-	V2
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukwila, WA 98188

statements | TILE & STONE

CC Mosaics - Lantern, Diamond, Herring & Brick

Porcelain Tile

Thickness: 6mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<=0.5%
Break Strength	C648	ISO-10545/4	Min. 290
Scratch Hardness	MOH's Scale	EN-101	2
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Group			2
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	-
PEI-Abrasion Resistance of Glazed Tile	C1027	ISO-10545/7	2
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.21
Shade and Texture Rating	CTDA "V"	-	V1
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukwila, WA 98188

statements | TILE & STONE

CC Mosaics - Octogonal

Porcelain Tile

Thickness: 6mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<=0.5%
Break Strength	C648	ISO-10545/4	Min. 290
Scratch Hardness	MOH's Scale	EN-101	3
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Group			3
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	-
PEI-Abrasion Resistance of Glazed Tile	C1027	ISO-10545/7	4
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.32
Shade and Texture Rating	CTDA "V"	-	V2
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukwila, WA 98188

statements | TILE & STONE

CC Mosaics - Penny Round Bright

Porcelain Tile

Thickness: 6mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<=0.5%
Break Strength	C648	ISO-10545/4	Min. 290
Scratch Hardness	MOH's Scale	EN-101	3
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Group			3
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	-
PEI-Abrasion Resistance of Glazed Tile**	C1027	ISO-10545/7	2-3-4-5
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.21
Shade and Texture Rating	CTDA "V"	-	V2
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

**PEI for Black is 2, Cobalt is 3, Gray is 4 and White is 5

Statements Tile & Stone

17600 W Valley Hwy

Tukwila, WA 98188

statements | TILE & STONE

CC Mosaics - Penny Round Matte

Porcelain Tile

Thickness: 6mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<=0.5%
Break Strength	C648	ISO-10545/4	Min. 290
Scratch Hardness	MOH's Scale	EN-101	3
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Group			3
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	-
PEI-Abrasion Resistance of Glazed Tile**	C1027	ISO-10545/7	4-5
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.36
Shade and Texture Rating	CTDA "V"	-	V2
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

**PEI for Gray is 4 and White is 5

Statements Tile & Stone

17600 W Valley Hwy

Tukwila, WA 98188

statements | TILE & STONE

CC Mosaics - Pin Wheel

Porcelain Tile

Thickness: 6mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<=0.5%
Break Strength	C648	ISO-10545/4	Min. 290
Scratch Hardness	MOH's Scale	EN-101	3
Chemical Resistance	C650	ISO-10545/13	Unaffected
Frost Resistance	C1026	ISO-10545/12	Resistant
Group			3
Deep Abrasion-Unglazed Tiles	C1243	ISO-10545/6	-
PEI-Abrasion Resistance of Glazed Tile	C1027	ISO-10545/7	4
Minimum Bond Strength (PSI)	C482	-	165
Dynamic Coefficient of Friction (DCOF)	A137.1	-	<=0.32
Shade and Texture Rating	CTDA "V"	-	V2
Facial Dimensions	C499	ISO-10545/2	Pass
Range of Thickness	C499	ISO-10545/2	Pass
Warpage/Surface Flatness	C485	ISO-10545/2	Pass
Wedging/Rectangularity	C502	ISO-10545/2	Pass

Statements Tile & Stone

17600 W Valley Hwy

Tukwila, WA 98188