

statements | TILE & STONE

Fuoritono - Polished

CIR Manifatture Ceramiche

Glazed Rectified Porcelain

Thickness: 9.5mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<0.3%
Break Strength	C648	ISO-10545/4	S>=1300N R>=35N/mm ²
Scratch Hardness	MOH's Scale	EN-101	>5
Chemical Resistance	C650	ISO-10545/13	A-LA-HA
Crazing Resistance	C424	ISO-10545/11	Resistant
Frost Resistance	C1026	ISO-10545/12	Resistant
PEI- Abrasion Resistance of Glazed Tiles	C1027	ISO-10545/7	3-Nero, Muschio 4-Gioglio 5-Bianco,Beige
Dynamic Coefficient of Friction (DCOF)	A137.1	-	Wet>0.42
Shade and Texture Rating	CTDA "V"	-	V4
Range of Thickness	C499	ISO-10545/2	+/- 5% +/- 0.5mm

Statements Tile & Stone

17600 W Valley Hwy

Tukwila, WA 98188

206-762-8181

Updated 7/2021

statements | TILE & STONE

Fuoritono - Matte

CIR Manifatture Ceramiche

Glazed Rectified Porcelain

Thickness: 9.5mm

	ASTM Test	ISO Test	Specifications
Water Absorption	C373	ISO-10545/3	<0.3%
Break Strength	C648	ISO-10545/4	$R \geq 35 \text{ N / mm}^2$
Scratch Hardness	MOH's Scale	EN-101	>6
Chemical Resistance	C650	ISO-10545/13	A-LA-HA
Crazing Resistance	C424	ISO-10545/11	Resistant
Frost Resistance	C1026	ISO-10545/12	Resistant
PEI- Abrasion Resistance of Glazed Tiles	C1027	ISO-10545/7	4-Biege, Giogio, Muschio, Nero 5-Bianco
Dynamic Coefficient of Friction (DCOF)	A137.1	-	Wet>0.42
Shade and Texture Rating	CTDA "V"	-	V4
Range of Thickness	C499	ISO-10545/2	+/- 5% +/- 0.5mm

Statements Tile & Stone

17600 W Valley Hwy

Tukwila, WA 98188